

Renolit Cramlington Ltd
Station Road
Cramlington
Northumberland
NE23 8AQ
Telephone: +44(0) 1670 718 222



Rely on it.

Customer: Foil Smart

Date: 5th July 2017

Background:

Samples of laminated profiles were sent to RCL for peel testing.

Summary:

The samples gave high consistent results which meet the current RAL GZ716 specification
All samples showed a foil break indicating an excellent bond

Investigation:

Peel testing was done on the samples of laminated profile provided

Results:

All samples snapped rather than peeled – peel adhesion results ranged from 4.21 to 4.54N/mm giving an average of 4.4N/mm




Figure 1: results from the eight peel adhesions

Conclusion:

Good results achieved – pass to the RAL specification GZ716

L Hagley

Date: 5th July 2017